



ARDEX WPM 163

(Sheltercoat DPM 163 Penetrative Sealer)

Single Component Polyurethane Dispersion Sealer

Requires only a short downtime for application. Trafficable within 24 hours

Penetrates and cures within the pores of the surface providing a seal for extended service life

Good flexibility properties to withstand substrate expansion and contraction

Can be applied to damp surfaces and freshly laid concrete

Non-flammable and very low odour

ARDEX Australia Pty Ltd
20 Powers Road
Seven Hills NSW 2147
Tel: (02) 9851 9199
Fax: (02) 9674 5621
Email: techinfo@ardexaustralia.com
Internet: www.ardex.com

ARDEX New Zealand Ltd
32 Lane St, Woolston
Christchurch, New Zealand
Tel: (03) 384 3029
Fax: (03) 384 9779
Email: techinfo@ardexaustralia.com
Internet: www.ardex.com

ARDEX WPM 163

(Sheltercoat DPM 163 Penetrative Sealer)

Single Component Polyurethane Dispersion Sealer

PRODUCT DESCRIPTION

ARDEX WPM 163 (Sheltercoat DPM163) is a one component water based urethane modified acrylic water resistant protective sealer that penetrates and cures within the pores of the surface being sealed. ARDEX WPM 163 is semi permeable allowing the surface to breathe and is not a waterproof membrane that will resist ponding water.

FEATURES/BENEFITS

- Interior or exterior use.
- Used as an Incontinence barrier for concrete floors in health care institutions.
- Water white and is stable to ultra violet exposure.
- Requires only short downtime for application. Four coats can be applied within the same day allowing light trafficking within 24 hours.
- Penetrates and cures within the pores of the surface being sealed to provide extended service life.
- Provides high abrasion resistance since the wear properties are dependent on the base substrate.
- Can be recoated at any time.
- Good flexibility properties to withstand substrate expansion and contraction.
- Non-flammable and very low odour.
- Surface tolerant and flexible.

TYPICAL USES

- As an economical single component sealer and dust suppressant for warehouse and showroom concrete floors to suppress dust formation and dirt collection with minimum down-time.
- As a water resistant sealer for external concrete or masonry walls to prevent water ingress while allowing the substrate to breathe to prevent internal surface condensation.
- As a grease and oil resistant sealer for concrete and masonry paths, paved areas, pool surrounds, etc.
- As an easily applied water resisting sealer for concrete, roof tiles, brick, stone, slate and masonry to inhibit water penetration
- As a protective sealer for sandstone to minimize dirt and atmospheric grime to develop while allowing the sandstone to breathe.
- As a sealer for timber wall paneling.

LIMITATIONS

The product should be applied whilst the surface temperature is between 10- 35°C. Drying time is adversely affected by low temperature and in situations where relative humidity is >85%.

Apply only using multiple thin film application.

Do not apply if rain is imminent.

DO not leave containers open for long period of time.

NOTE: Sealing a surface will decrease slip resistance in wet conditions.

SURFACE PREPARATION

All surfaces must be cleaned free from dust, dirt, grease, oil, previous surface coatings or adhesive and other surface contaminants.

ARDEX WPM 163 is a clear sealer and any contamination, surface texture irregularities, or stains existing at the time of coating will be evident, and probably emphasised, in the final finish.

APPLICATION

Thoroughly mix the product before use. ARDEX WPM 163 may be applied by brush, roller or low volume spray application techniques and should be applied in multiple thin films only to allow for maximum penetration allowing 30 minutes to 1 hour at 25°C between coats.

Care should be taken not to apply excess material in each coat when using brush or roller. Application of excess material per coat will result in the product bridging the pores preventing penetration.

ARDEX WPM 163 should preferably be applied to damp or moist substrates that are surface dry and not wet. Excess water in the substrate will hinder the penetration of the product.

The number of coats required will vary depending on the porosity of the substrate. Apply sufficient material to fill all surface pores. Two coats are normally sufficient on steel trowelled concrete while clay pavers are likely to require four coats.

Allow 24 hours curing before subjecting to light pedestrian traffic, three days for rubber wheeled traffic, seven days for full cure and maximum traffic loading.

CLEANING & THINNING

ARDEX WPM 163 normally does not require thinning for application. For very fine grained substrates, thin with up to 10% of fresh clean water.

Wash all equipment in warm water or water/detergent immediately on completion of the work.

PROPERTY DATA

Colour	Clear/water white
Finish	Semi-gloss going to mat with external exposure aging
Typical coverage	15m ² /L/coat depending on the porosity of the substrate
Typical no. of coats	2-4 depending on the substrate porosity & surface finish desired
Recoat time	_ to 1 hr @ 25°C & 50% R.H.
Full cure	7 days @ 25°C & 50% R.H.
UV Exposure	Resistant

SAFETY PRECAUTIONS

ARDEX WPM 163 is non-hazardous; non-dangerous goods.

Avoid contact with skin and eyes and avoid breathing vapour or spray mist. Wear eye protection and protective gloves when mixing and using.

FIRST AID

If poisoning occurs, contact a doctor or the Poisons Information Centre. If swallowed, do NOT induce vomiting. Give a glass of water. If skin contact occurs, remove contaminated clothing and wash skin thoroughly. If in eyes, hold eyes open, flood with water for at least 15 minutes and see a doctor.

ADDITIONAL INFORMATION IS LISTED IN THE MATERIAL SAFETY DATA SHEET.

DISCLAIMER

The technical details, recommendations and other information contained in this data sheet are given in good faith and represent the best of our knowledge and experience at the time of printing. It is your responsibility to ensure that our products are used and handled correctly and in accordance with any applicable Australian Standard, our instructions and recommendations and only for the uses they are intended. We also reserve the right to update information without prior notice to you to reflect our ongoing research and development program.

Country specific recommendations, depending on local standards, codes of practice, building regulations or industry guidelines, may effect specific installation recommendations.

The supply of our products and services is also subject to certain terms, warranties and exclusions, which may have already been disclosed to you in prior dealings or are otherwise available to you on request. You should make yourself familiar with them.

ARDEX Australia Pty Ltd

New South Wales	Ph (02) 9851 9100	Fax (02) 9838 7970
Queensland	Ph (07) 3817 6000	Fax (07) 3881 3188
Victoria/Tasmania	Ph (03) 9308 9255	Fax (03) 9308 9332
South Australia	Ph (08) 8268 2511	Fax (08) 8345 3207
Western Australia	Ph (08) 9256 8600	Fax (08) 9455 1227

ARDEX New Zealand Ltd

Auckland	Ph (09) 5800 005	Fax (09) 5799 963
Wellington	Ph (04) 5685 949	Fax (04) 5686 376
Christchurch	Ph (03) 3843 029	Fax (03) 3849 779

Technical Services Toll Free: 1800 224 070

Date: July 2007